



TEST REPORT

Report No: 232016025288

**Applicant: SHANGHAI FIRST-TRUST
INTERNATIONAL CO.,LTD**

Zhejiang Academy of Science and Technology for Inspection and Quarantine



TEST REPORT


Report No: 232016025288

Date: 2016-06-17

The following information supplied by the client:

Sample information	Sample Name:	Nylon Mesh	
	Specifications:	nylon mesh for tea bags	
	Brand Name:	Iris peacock	
	ID:	/	
	Sample Quantity:	20 PCS	
Client information	Applicant:	SHANGHAI FIRST-TRUST INTERNATIONAL CO.,LTD	
	Address:	8th Floor ,No.1 Kangqiaodong Rd.Pudong,Shanghai,China	

The following information confirmed by ZAIQ:

Test Information	Sample Name:	Nylon Mesh		
	Test Photo:			
	Date of Sample Received:	2016-06-12	Test Period:	2016-06-12 ~2016-06-16
	Judgment Method:	1. GB 16332-1996		
Conclusion	This report only provides experimental data and individual judgment, as shown in the test results page			

*****End of the Page****

Note: The test report is only responsible for the sample mentioned above. And the report shall not be reproduced except in full, without written approval of the laboratory.



TEST REPORT

Report No: 232016025288

Date: 2016-06-17

Test Results:

Test Items	Judgment Method	Conclusion
Evaporation Residue (4% Acetic Acid 60°C 30min)	GB 16332-1996	PASS
Evaporation Residue(Hexane 20°C 1h)		PASS
Consumption Of Potassium Permanganate (Water 60°C 30min)		PASS
Heavy Metal(Count As Lead) (4% Acetic Acid 60°C 30min)		PASS
Decolor Test (Soak)		PASS
Decolor Test (Buffet Oil)		PASS
Decolor Test (Ethanol)		PASS
Caprolactam		PASS

Remarks: 1. Pass—the results comply with the limits as set by the judgment method.

2. Specific results: refer to the next table.

***** End of the Page*****

Note: The test report is only responsible for the sample mentioned above. And the report shall not be reproduced except in full, without written approval of the laboratory.



TEST REPORT

Report No: 232016025288

Date: 2016-06-17

Test Results:

Test Items	Test Method	Limit	Unit	Results
1 Evaporation Residue (4% Acetic Acid 60°C 30min)	GB/T 5009.60-2003	30	mg/L	19
2 Evaporation Residue (Hexane 20°C 1h)		30	mg/L	<10
3 Consumption Of Potassium Permanganate (Water 60°C 30min)		10	mg/L	<2
4 Heavy Metal(Count As Lead) (4% Acetic Acid 60°C 30min)		1	mg/L	<1
5 Decolor Test (Soak)		Negative	---	Negative
6 Decolor Test (Buffet Oil)		Negative	---	Negative
7 Decolor Test (Ethanol)		Negative	---	Negative
8 Caprolactam		GB/T 5009.125-2003	15	mg/L

AUTHORIZED SIGNATURE: _____



阮毅

*** End of the Page***

*** End of the Report***

Note: The test report is only responsible for the sample mentioned above. And the report shall not be reproduced except in full, without written approval of the laboratory.